

# Zinc Spray bright grade



## long-term cathodic corrosion protection

Zinc Spray „bright grade“ is approved by the German TÜV and provides a longlasting cathodic corrosion protection to all metal surfaces. It has a bright colour shade matched to hot galvanization.

The spray forms a fast-drying, adherent protective layer of microfine zinc flakes. The zinc flakes form a resistant protective layer, even under extreme weather and environmental conditions.

Zinc Spray „bright grade“ can be used for the coating of welded joints and drilled holes, as a conductive intermediate layer for spot welding and everywhere where metal must be protected against corrosion.



## Technical Data

Colour	corresponds approximately to RAL 9006, "Fresh hot-dip galvanisation"
Application	indoors and outdoors
Binding agent	modified alkyd resin
Pigment	flaky zinc and aluminium pigments
Pigment purity	approx. 99,9% Zn / approx. 99,5% Al
Percentage of metal in dry film	70 %
Specific weight	1,0 - 1,2 g/cm <sup>3</sup>
Recommended primer	Zinc-Spray
Processing temperature	+5 to +35, optimal +18 to +35 °C
Consumption at 1.5 cross coats	150 ml/m <sup>2</sup>

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Layer thickness at 1.5 cross coats	30 - 50 µm
Dust dry after	15 min.
Hardened after	12 h
Overpaintable after	24 h
Abrasion-resistant yes/no	abrasion-resistant
Cross cutting DIN 53151/ ISO 2409	cross cut characteristic value GT 0 to GT 1
Salt spraying test DIN 50021/ DIN 53167	>550 h
Mandrel bend test DIN EN ISO 1519	no hair cracking
Top coating	not required
Storage stability	24 months
Temperature resistance	-50 to +300 °C
ISSA-Code	53.402.07
IMPA-Code	45 08 12

\*corresponds approximately to the specified RAL colours

## Surface pre-treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

## Processing

Shake can before use until the mixing ball can be heard clearly. Spray on evenly and crosswise at room temperature (approx. 20°C) and at about 25 cm distance from the surface. Dust-dry after approx. 15 minutes, fully hardened after approx. 10-12 hours.

## Storage

Pressurized container: protect from sunlight and do not expose to temperatures exceeding +50°C.

## Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Available sizes:

11001400 Zinc Spray bright grade 400 ml

## Accessories:

11207400 Surface Cleaner, 400 ml  
11850200 Hand Protective Foam, 200 ml

WEICON GmbH & Co. KG  
(Headquarters)  
Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca  
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr  
www.weicon.com.tr

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weiconcz.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es